CIVIL TECH LABS

Accredited by NABL as per ISO/ IEC 17025 : 2005

5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867 / Mob. : 96862 31801, Email: civiltechlabs@gmail.com

T-2654

To,

Assistant Executive Engineer
Yelahanka Satellaite Town Sub Division,
BBMP Bangalore.

20th February 2015

Dear Sir,

Sub: Construction of Concrete roads to Sihi Neeru Raste and RCC drain at Kanakanagara in Ward No. 04.
Testing of cubes – Reg.

As requested the 07th day Compressive Strength Test of Cubes was carried out for the above work for the samples supplied by you.

Please find the enclosed Test Report of the above.

Thanking you,

For Civil Tech Labs,

Khushboo

CIVIL TECH LABS BANGALORE

(KHUSHBOO L.)
Quality Manager

CIVIL TECH LABS
#5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Construction of Concrete roads to Sibi Neem Raste and RCC drain at Kanakanagara in Ward No. 04.
Name of Agency	Sri. R. Sathish, Contractor
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed: 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	CC Work (Drain)	13/02/2015	20/02/2015	7	8.16	338	**15.02**	**15.11**
2					8.19	342	**15.20**	
3					8.18	340	**15.11**	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Construction of Concrete roads to Sihi Neeru Raste and RCC drain at Kanakanagara in Ward No. 03
Name of Agency	Sri. R. Sathish, Contractor.
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm^2
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm^2)	Avg Compressive Strength (N/mm^2)
1	CC Work (Covering Slab)	11/02/2015	18/02/2015	7	8.19	352	15.64	15.56
2					8.18	350	15.56	
3					8.17	348	15.47	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

Accredited by **NABL** as per ISO/ IEC 17025 : 2005

5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027

Ph: 080 - 4114 2867 / Mob. : 96862 31801, Email: civiltechlabs@gmail.com

T-2654

To,

Assistant Executive Engineer
Yelahanka Satellaite Town Sub Division,
BBMP Bangalore.

26th February 2015

Dear Sir,

Sub: Construction of Concrete roads to Sihi Neeru Raste and RCC drain at Kanakanagara in Ward No. 04.
Testing of cubes – Reg.

As requested the 07th day Compressive Strength Test of Cubes was carried out for the above work for the samples supplied by you.

Please find the enclosed Test Report of the above.

Thanking you,

For Civil Tech Labs,

Khushboo

CIVIL TECH LABS BANGALORE

(KHUSHBOO L.)
Quality Manager

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Construction of Concrete roads to Sibi Neeru Raste and RCC drain at Kanakanagara in Ward No. 04.
Name of Agency	Sri. R. Sathish, Contractor.
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	CC Work (Pavement)	19/02/2015	26/02/2015	7	8.18	352	**15.64**	**15.61**
2					8.17	348	**15.47**	
3					8.19	354	**15.73**	

Note:
1. The results relate only to the items tested
2. Report shall not be reproduced except in full, without the written approval of the lab
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Construction of Concrete roads to Sibi Neera Raste and RCC drain at Kamakamagara in Ward No 04.
Name of Agency	Sri. R. Sathish, Contractor
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	CC Work (Pavement)	18/02/2015	25/02/2015	7	8.18	342	15.20	15.20
2					8.20	344	15.29	
3					8.19	340	15.11	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS
5, 1st Cross, Srinivasa Colony, Mission Road, Bangalore - 560027
Ph: 080 - 4114 2867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE, Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Construction of Concrete roads to Sibi Neeru Raste and SCC drain at Kanakanagara in Ward No 04.
Name of Agency	Sri. R. Sathish, Contractor
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg Compressive Strength (N/mm²)
1	CC Work (Pavement)	17/02/2015	24/02/2015	7	8.18	336	14.93	15.26
2					8.20	352	15.64	
3					8.19	342	15.20	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

Colony, Mission Road, Bangalore - 560027
9867, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	M/s. Yelahanka Satellite Town Sub Division, BBMP
Name of Work	Providing Iron of Concrete roads to Sahi Nevru Pass and RCC drain at Kanakanagara in Ward No. [illegible]
Name of Agency	Sri. P. Sathish, Contractor
Grade of Concrete	M-20
No. of cubes tested	3
Dimension of Specimen	150mm x 150mm x 150mm
Cross Sectional Area	22500 mm²
Technical Reference	IS: 516-1959 (Reaffirmed 2004)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm²)	Avg. Compressive Strength (N/mm²)
1	CC Work (Pavement)	16/02/2015	23/02/2015	7	8.1x	352	15.64	15.56
2					8.1x	348	15.47	
3					8.17	350	15.56	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the la
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Lab Incharge
Civil Tech Labs